Indication

Cavex Impressional is a dustfree alginate impressional material with a creamy consistency. It is available in Normal Set and Fast Set and suitable both for general dental practice and for orthodontics. It has exceptional good elastic properties and a high tear-resistance which makes it even more suitable for orthodontics. Thanks to the blue colour the impression is very good readable. The impression surface is very smooth, which gives an excellent gypsum compatibility. The appropriate alginate to combine with Cavex Combiloid (Hydrocolloid).

Storing Cavex Impressional

- Always store Cavex Impressional in a cool, dry place.
- After opening the packaging store Cavex Impressional in a firmly closed storage box. Always close the box immediately after using the material.

Dosing

- Stir the powder to loosen it well.
- Scoop it from the storage box with a light, swift movement and then stroke the powder smooth: do not compress the powder in the scoop.
- Mix water (at room temperature) and powder in the mixing cup.

* for a partial impression 1 scoop + 1/3 beaker of water * for a full impression 2 scoops + 2/3 beaker of water * for an extra-large impression 3 scoops + full beaker of water

* for stiff alginate (1) 3 scoops + water (high viscosity level)

Ideal mixing ratio: 19.3 g = 3 measuring scoops: 46 ml = 1 full beaker. You can make the mixture thinner or thicker by adding more or less water respectively.

(1) Cavex stiff alginate technique

The impression technique to make an accurate first (functional) impression for a stable denture. It is the combination of an impression tray with rimlock for edentulous jaws eg Schreinemakers "full denture tray system" and stiff (high viscosity) Cavex alginate. Stiff alginate is the normal amount of powder with 30% less water. The high viscosity alginate pushes the soft tissue aside As a result the anatomical details, even the frenae are clearly visible. The gypsum model can be lined-out accurately and fully, which enables the dental technician to ensure that the individual tray is a perfect fit. The result: a stable denture and satisfied patient.

Mixing

- Mix both components together carefully and thoroughly for 30 seconds until a a smooth and homogeneous mixture is obtained.
- Fill the tray immediatedly and use a wettened finger to stroke it smooth.
- Make sure that the patient has rinsed the mouth with warm water in the mean time.

Taking the impression

- Within 1½ minute (Normal Set) / 1 minute (Fast Set) after mixing, insert the filled impression tray into the patient's mouth applying gentle pressure.
- Allow the impression material to set in the mouth for 1½ minute (Normal Set) / 1 minute (Fast Set).
- Remove the tray from the mouth in a single rapid movement.
- Rinse the tray under cold running water to remove saliva and any residues.
- Remove any excess water, but leave the surface moist. Never blow-dry!

Making the plaster models

- Immediately after rinsing, pour out the plaster impression and make a second plaster model if desired.
- If immediate pouring is impossible: store the impression in a firmly sealed plastic bag to achieve a relative humidity of 100%. This is essential for optimum results at a later pouring.
- Make the plaster model within 48 hours after taking the impression.

For preference, use one of the following plaster products:

Type 3: Moldano® (Heraeus Kulzer)

Type 4: Moldastone®, Moldasynt® (Heraeus Kulzer)

Product specifications

Cavex Impressional (Normal Set / Fast Set) meets the EN 21563 (= ISO 1563) and ADA 18 standards.

| | ISO 1563* | Cavex Impressional | | |
|--|-----------|--------------------|-----------|--------|
| | | Normal Set | | |
| Powder / water ratio | - | 19,3 / 46 | 19,3 / 46 | g / ml |
| Mixing time | < 60 | 30 | 30 | sec. |
| Total working time according to anufacturer's | | 2 | 1.30 | min. |
| indication | | | | |
| Total setting time according to manufacturer's | | 3.30 | 2.30 | min. |
| indication | | | | |
| Compression strength | > 0.35 | 1.00 | 1.10 | MPa |
| Recovery after distortion | > 95 | 97.0 | 96.9 | % |
| Elastic distortion | 5-20 | 15.4 | 15.8 | % |
| Detail reproduction | 50 | 25 | 25 | μm |

^{*} measured with deionised water at 23°C

Mixing scheme Cavex Impressional

| | mix | filling + placing | | setting in mouth | | |
|------------------------|-------------------|-----------------------------|------|------------------|--|--|
| Normal Set | 30 sec. | 1 minute 30 sec. | | 1 minute 30 sec. | | |
| Fast Set | 30 sec. | 1 minute | 1 mi | nute | | |
| Normal Set Fast Set | total work | 2 minuten minute 30 sec. | | | | |
| Normal Set | 3 minutes 30 sec. | | | | | |
| Fast Set | | 2 minutes 30 s | | | | |

Note:

- 1. The working/setting times increase with a lower (water) temperature. At higher temperatures the times become shorter.
- 2. The water hardness has the same effect: the harder the water used for mixing, the shorter the working/setting time.

Our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses.

The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide consistent quality of our products within the scope of our General Conditions of Sale and Delivery.